

INP nach DIN / EN 10024 Schmale Reihe

INP	HG	Abmessungen in mm				F	Jx-x	Wx-x	ix-x	Jy-y	Wy-y	iy-y
		kg/m	h	b	s = r1							
80	6,1	80	42	3,9	5,9	7,6	77,8	19,5	3,20	6,3	3,00	0,91
100	8,5	100	50	4,5	6,8	10,6	171	34,2	4,01	12,2	4,88	1,07
120	11,5	120	58	5,1	7,7	14,2	328	54,7	4,81	21,5	7,41	1,23
140	14,7	140	66	5,7	8,6	18,3	573	81,9	5,61	35,2	10,70	1,40
160	18,5	160	74	6,3	9,5	22,8	935	117,0	6,40	54,7	14,80	1,55
180	22,5	180	82	6,9	10,4	27,9	1450	161,0	7,20	81,3	19,80	1,71
200	27,0	200	90	7,5	11,3	33,5	2140	214,0	8,00	117,0	26,00	1,87
220	32,0	220	98	8,1	12,2	39,6	3060	278,0	8,80	162,0	33,10	2,02
240	37,0	240	106	8,7	13,1	46,1	4250	354,0	9,59	221,0	41,70	2,20
260	43,0	260	113	9,4	14,1	53,4	5740	442,0	10,40	288,0	51,00	2,32
280	49,0	280	119	10,1	15,2	61,1	7590	542,0	11,10	364,0	61,20	2,45
300	56,0	300	125	10,8	16,2	69,1	9800	653,0	11,90	451,0	72,20	2,56
320	63,0	320	131	11,5	17,3	77,8	12510	782,0	12,70	555,0	84,70	2,67
340	70,0	340	137	12,2	18,3	86,8	15700	923,0	13,50	674,0	98,40	2,80
360	78,0	360	143	13,0	19,5	97,1	19610	1090,0	14,20	818,0	114,00	2,90
380	86,0	380	149	13,7	20,5	107,0	24010	1260,0	15,00	975,0	131,00	3,02
400	95,0	400	155	14,4	21,6	118,0	29210	1460,0	15,70	1160,0	149,00	3,13
425	106,0	425	163	15,3	23,0	132,0	36970	1740,0	16,70	1440,0	176,00	3,30
450	118,0	450	170	16,2	24,3	147,0	45850	2040,0	17,70	1730,0	203,00	3,43
475	131,0	475	178	17,1	25,6	163,0	56480	2380,0	18,60	2090,0	235,00	3,60
500	145,0	500	185	18,0	27,0	180,0	68740	2750,0	19,60	2480,0	268,00	3,72
550	171,0	550	200	19,0	30,0	213,0	99180	3610,0	21,60	3490,0	349,00	4,02
600	203,0	600	215	21,6	32,4	254,0	139000	4630,0	23,40	4670,0	434,00	4,30